



NatureOne® Renew

PRODUCT DATA

A superior VOC compliant non-pigmented exterior finish designed as a clear maintenance coat over existing NatureColor® or NatureOne® exterior three-coat protection system. NatureOne® Renew refreshes the pigmented protection system that is already in place on vertical surfaces without darkening the wood.

Color Range
Clear 300

Packaging
Available in US Gallons

Shelf Life & Storage
Approximately 5 years in an unopened container.
Keep from freezing.

Properties
Viscosity: 400-450 Cps
Density: 8.69 +/- 0.25 U.S. Gal
Solids by Weight: 38.26% +/- 2%
Solid by Volume: 35.35% +/- 2%
Gloss Level: Satin finish (35-40 G.U.)
V.O.C. 132 g/L – water free
UV Protection: Three pronged protection
Flow: Good
Durability: Excellent, subject to adequacy of initial application film thickness (approx. 35 microns when dry), timely recoat maintenance, quality of construction, method of application, etc.
SDS Sheets available at www.structureswoodcare.com

Features and Benefits
Non-pigmented.....Designed to provide a clear non-darkening maintenance coat.
Micro-porous.....Allows moisture in the wood to escape.
UV protection.....Screens the wood from sunlight deterioration through use of Three-pronged protection.
Adhesion promoters...Provide excellent adhesion to existing alkyd and water based finishes.
Water repellent.....Protects against damage from moisture intrusion.
Fungi resistant.....Impedes the growth of wood disfiguring and decaying micro-organisms.
Flexible.....Allows for expansion and contraction of the wood.
Water based.....Easy clean up with soap and water, dries quickly.
VOC compliant.....Environmentally friendly.

Where to Use
NatureOne® Renew is used as a clear maintenance coat over vertical surfaces that have been coated with NatureColor® or NatureOne® exterior three-coat protection system. This single coat maintenance product restores the original protection system while retaining the same look and color of the wood. Surfaces must be in good condition.
<ul style="list-style-type: none"> • Sidings – Solid Wood, Composite • Entry Doors and Garage Doors • Shakes • Timbers and Logs • Trim • Shutters
*Not recommended on bare wood, fences or horizontal surfaces.

Surface Preparation
1. Wet the surface with clean water.
2. Use a garden pump sprayer to saturate the surface with a mixture of two (2) ounces of Tri-sodium Phosphate (TSP) or phosphate free substitute added to one quart liquid household bleach, added to every three quarts of warm water needed for cleaning.
3. Keep the surface wet with this moisture 15 to 20 minutes. Lightly scrub the surface with a stiff bristle brush to assist in removing dirt and mildew spores.
4. Thoroughly power wash the moisture off, working from the top to bottom, using a fan spray at no more than 500 PSI. The washer nozzle must be 12 inches from the surface for best results. The use of higher pressure may result in damage to the wood.
5. Allow at least three continuous days of dry weather before application of NatureOne® Renew. Fill all joints, cracks & nail holes if needed with a quality polyurethane or acrylic caulk.

Coverage

Varies with wood species and its porosity.

Textured/Rough Sawn Wood:

175-300 sq ft per gal.

Smooth wood:

300-400 sq ft per gal.

Drying Time

Dry in 2 hours.

Low temperatures or high humidity may extend dry times.

Clean Up

Clean spills and spatters immediately with soap and water.

Clean equipment immediately after use with soap and water.

Dispose of empty can or unused finish in accordance with state and federal regulations.

Distributed By:

Schroeder Log Home Supply, Inc.

1-800-359-6614 www.loghelp.com

Application Method

1. Do a one coat sample test to ensure satisfaction with results. Apply over vertical surfaces that have been coated with NatureColor® or NatureOne® exterior three coat protection system. Surfaces must be in good condition.
2. Surface must be dry. Do not apply when surface is too hot to touch. Avoid working in the sun.
3. Need to scuff sand with 60-80 grit sandpaper.
4. Stir material thoroughly before and during use.
5. Best results are with a quality nylon polyester brush.
Airless sprayer application is acceptable, but must be immediately back brushed. Tip: 5-15 to 5-17 Pressure: 1000 to 1500 PSI
6. Generously coat the surface; saturate end grains, nail holes, minor cracks and cavities. Apply as liberally as possible without runs – do not “stretch out” the product. Apply in the direction of the grain. On textured/rough sawn surfaces, thoroughly cross brush to soak the finish into the surface and finish brushing in the direction of the grain. If spraying, spray until the coating runs slightly and then immediately back brush.
7. Avoid lap marks by starting at one end of a given surface area and while maintaining a wet edge, follow through to the opposite end of the surface area.

For Best Performance

- Keep material from freezing
- Do not thin or add colorants
- Apply product to vertical surfaces that have been coated with NatureColor® or NatureOne® 100% Acrylic three coat protection system. Surface must be in good condition and have been maintained according to Structures Wood Care’s specs.
- Apply when wood surface moisture is not more than 18%.
- To avoid dirt contamination and cell loss adhesion, coat vertical surfaces within two weeks of surface preparation.
- Stir thoroughly before and during application. Do not shake.
- Apply liberal coats.
- Apply in the direction of the grain.
- Maintain a wet edge.
- Saturate all end grains, nail holes, minor cracks, etc.
- Apply when surface and air temperature are between 50°F and 85°F
- Avoid application when dew or moisture is present.
- Avoid applying finish in the direct sun or when surface is hot to touch.
- Power rinsing your building once a year will clean off the dirt and dust and enhance the performance of the coating.
- Apply your first maintenance coat sooner than later – see spec guide



24530 Hazelwood Drive P.O. Box 599 Nisswa MN 56468

Phone: 218.963.4680 Fax: 218.963.4689 Toll Free: 866.963.4680

www.Structureswoodcare.com